



For high traffic areas that require a durable and easy to maintain surface, **OmniGuard** is the obvious choice. The high solid formulation of this UHS floor finish produces extreme gloss that withstands the effects of crowded market places in any weather condition.

DIRECTIONS

Read all directions and Safety Data Sheets (SDS) before using.

1. For a floor that has been stripped, properly neutralized, rinsed and allowed to dry thoroughly, apply 4-5 thin coats using a clean synthetic mop. Allow the floor to dry thoroughly between coats and prior to burnishing.
2. Optional: Apply 2 thin coats of floor sealer for old or porous floors or for high traffic areas, then apply 2-3 coats of finish.
3. For a floor that has been deep scrubbed and allowed to dry thoroughly, apply 1-2 thin coats using a clean synthetic mop. Allow floor to dry thoroughly between coats and prior to burnishing.

PRODUCT INFO

Product Code	141FS	141FSE	141MPE	141DR
Volume	2.50 US gallons	10 liters	4 liters	55 US gallons
Shipping Package	2 x 2.5 gallons	2 x 10 liters	4 x 4 liters	per unit
Pallet Quantity	48	48	48	4

SURFACES



TECHNICAL DATA

Description	Polymer emulsion
Appearance	Milky white
Specular Gloss (60°) ASTM D1455-87 (2008)	>85
Viscosity (Brookfield) @ 68°F (20°C)	<10 centipoise
Coverage Rate	2500 to 3000 ft ² /gal 61 to 74 m ² /liter
Dry Time	About 25 minutes
Buffability	Excellent
Removability ASTM D1792-06	Excellent
VOC 40 CFR Part 59 Subpart C	0.06%
Non-Volatile Solids ASTM D2834-95 (2008)	25%
Fragrance	Mild odor, no fragrance added
Slip Resistance ULTM410	Meets requirements
Shelf Life ASTM D1791-93 (2008)	1 year
Density ASTM D1475-98 (2008)	8.5 lb/gal @ 68°F 1.03 kg/L @ 20°C
Detergent Resistance ASTM D3207-92 (2008)	Excellent
Freeze/Thaw ASTM D3209-93 (2008)	Passes 3 cycles
Container	2.5 US gal/9.5 L (FS packaging) 2.64 US gal/10 L (FSE packaging) 1.06 US gal/4 L (MPE packaging) 55 US gal/208 L (DR packaging)



Floor Coating and Finishing materials
as to slip resistance only.

42E6